

January 20, 1993

Universal magnetic properties of $La_{2-\delta}Sr_{\delta}CuO_4$ at intermediate temperatures.

Andrey V. Chubukov^{1,2} and Subir Sachdev¹

¹*Departments of Physics and Applied Physics, P.O. Box 2157,*

Yale University, New Haven, CT 06520,

and ²P.L. Kapitza Institute for Physical Problems, Moscow, Russia

We present the theory of two-dimensional, clean quantum antiferromagnets with a small, positive, zero temperature (T) stiffness ρ_s , but with the ratio $k_B T/\rho_s$ arbitrary. Universal scaling forms for the uniform susceptibility (χ_u), correlation length(ξ), and NMR relaxation rate ($1/T_1$) are proposed and computed in a $1/N$ expansion and by Monté-Carlo simulations. For large $k_B T/\rho_s$, $\chi_u(T)/T$ and $T\xi(T)$ asymptote to universal values, while $1/T_1(T)$ is nearly T -independent. We find good quantitative agreement with experiments and some numerical studies on $La_{2-\delta}Sr_{\delta}CuO_4$.

The last few years have seen extensive theoretical and experimental studies of two dimensional quantum Heisenberg antiferromagnets, with particular attention to the antiferromagnetism in the cuprate compounds [1,2]. On the theoretical side, most notable has been the work of Chakravarty *et.al.* [3] who focused mainly on the low temperature (T) properties of systems with well established long-range Néel order at $T = 0$; their most detailed results were in a regime in which the fully renormalized, $T = 0$, spin-stiffness ρ_s , was not too small, while the temperature satisfied $k_B T \ll \rho_s$. Under these conditions, the antiferromagnet could be treated as a classical system, with all effects of quantum fluctuations being absorbed into renormalization of the couplings. At low T , there has been good agreement between their results and experiments on La_2CuO_4 [3]. However, the experimental results at higher T remain poorly understood - there are clear deviations from the classical behavior and it is expected that quantum fluctuations will play a more fundamental role. Besides, in the lightly-doped cuprates, ρ_s is likely to be quite small, thus decreasing the T range over which the renormalized-classical behavior will hold. Finally, there are experimental realizations of frustrated two-dimensional Heisenberg antiferromagnets [4], which, in all likelihood, have a very small value of ρ_s .

Our understanding of the experiments would clearly be improved by precise theoretical predictions in low temperature regimes other than $k_B T \ll \rho_s$. To this end, we discuss here some universal properties of clean two-dimensional quantum Heisenberg antiferromagnets, with nearest-neighbor exchange J , in which the stiffness ρ_s is ‘small’, but non-zero. We will study the physics when $0 < \rho_s \ll J$, $k_B T \ll J$, but the ratio $k_B T / \rho_s$ is allowed to be *arbitrary*. The system is then controlled by renormalization-group flows near the the $T = 0$ quantum fixed-point separating the Néel ordered and quantum-disordered phases. Our main new result will be that, in this regime, the absolute values of the entire long-wavelength, low-frequency, uniform and staggered spin susceptibilities are completely universal functions of just three thermodynamic parameters: ρ_s , c , and the ordered staggered moment N_0 . The universal functions depend *only* on the symmetry of the order parameter, and sensitivity to all lattice-scale physics arises only through the values of ρ_s , c , and N_0 . For small $k_B T / \rho_s$,

the T -dependence of our results is similar to those already obtained in Ref. [3]. For large $k_B T/\rho_s$, most of our results are new. We will show that they are consistent with the available experimental [5,6,7] and some of the numerical [8,9,10] data on the uniform susceptibility, correlation length and NMR relaxation rate for undoped and weakly-doped $La_{2-\delta}Sr_\delta CuO_4$. We thus argue that the use of a ‘small’ ρ_s point-of-view is not unreasonable even for the pure square lattice, spin-1/2, Heisenberg antiferromagnet; while ordered at $T = 0$, this system is evidently close to the point where long-range-order vanishes.

Our results follow from some very general properties of the $T = 0$ quantum fixed-point separating the magnetically-ordered and quantum-disordered phases. These properties are expected to be valid in both undoped and doped antiferromagnets, though not in the presence of randomness [11,12]. They are (i) the fixed point is described by a continuum 2+1 dimensional field theory which is ‘Lorentz’-invariant, and the spin-wave velocity, c , remains non-singular through the phase transition (ii) at $T = 0$, on the magnetically ordered side, there is a Josephson correlation length ξ_J which diverges at the quantum fixed-point; near this fixed point ρ_s equals $\hbar c \Theta / \xi_J$ where Θ is a universal number [13,14]; and (iii) Turning on a small T places the critical field theory in a ‘slab’ geometry which is infinite in the two spatial directions, but of finite length $L_\tau = \hbar c / (k_B T)$, in the imaginary time (τ) direction - its consequences therefore follow from finite-size scaling.

Uniform susceptibility, χ_u : We first consider the response of the antiferromagnet to a static, spatially uniform, external magnetic field (the extension to a field at finite wavevector k or frequency ω will be omitted here for brevity). Such a field causes a uniform precession of all the spins, which can be removed by transforming to a rotating reference frame at the price of a twist in the boundary conditions along the τ direction [15]. The response of the system to this twisted boundary condition defines a stiffness, ρ_τ , which equals χ_u . However, the fixed point is Lorentz invariant, and hence χ_u has the same scaling properties as ρ_s . Application of finite-size scaling [16] then yields the following T dependence for χ_u

$$\chi_u(T) = \left(\frac{g\mu_B}{\hbar c} \right)^2 k_B T \Omega_Q(x) \quad ; \quad x \equiv \frac{N k_B T}{2\pi \rho_s} \quad (1)$$

where $g\mu_B/\hbar$ is the gyromagnetic ratio, N is the number of components of the order parameter, and $\Omega_Q(x)$ is a *universal* function. Note $x \propto \xi_J/L_\tau$, the length-ratio expected in finite-size scaling functions. We have computed $\Omega_Q(x)$ in a $1/N$ expansion for the $O(N)$ non-linear sigma model in 2+1 dimensions [17]. The $O(3)$ model describes the low-energy dynamics of two-dimensional Heisenberg antiferromagnets on a square lattice. The antiferromagnet also carries Berry phases, not present in the σ -model, but these have been argued to be irrelevant at the quantum fixed-point [11]. At $N = \infty$, the scaling function $\Omega_Q(x)$ can easily be calculated:

$$\Omega_Q^{N=\infty}(x) = \frac{1}{\pi x} + \frac{\sqrt{4 + e^{-2/x}}}{2\pi e^{-1/x}} F(x)$$

$$F(x) \equiv 2 \operatorname{arcsinh}((1/2)e^{-1/x}) \quad (2)$$

Of particular interest is the behavior of χ_u for large x . The function $\Omega_Q^{N=\infty}(x)$ is analytic at $x = \infty$, and the general principles of finite-size scaling [16] suggest that this remains true at finite N . Thus we expect that $\Omega_Q(x \rightarrow \infty) = \Omega_\infty + \Omega_1/x + \dots$ with Ω_∞ , Ω_1 universal numbers. Combined with (1), this implies that a plot of $\chi_u(T)$ vs. T will be straight line at large T/ρ_s with universal slope and intercept, whose values are related to Ω_∞ and Ω_1 respectively. At $N = \infty$ we obtain from (2), $\Omega_\infty = (\sqrt{5}/\pi) \ln [(\sqrt{5} + 1)/2] \approx 0.3425$ and $\Omega_1 = 4\Omega_\infty/5$. We have computed the first $1/N$ correction to Ω_∞ and indeed found that it is a universal, regularization-independent number. We obtained

$$\Omega_Q(x = \infty) \equiv \Omega_\infty = 0.3425(1 - 0.63/N + \dots). \quad (3)$$

We have also performed Monté-Carlo simulations of a *classical* $D = 3$ Heisenberg ferromagnet on a cubic lattice, whose phase transition is expected to be in the same universality class as the $O(3)$ sigma model. We used a lattice of size $L \times L \times L_\tau$ ($L \leq 30$, $L_\tau \leq 10$) at its known critical coupling [18] and computed ρ_τ . It then follows that $\Omega_\infty = \lim_{L_\tau \rightarrow \infty} \lim_{L \rightarrow \infty} L_\tau \rho_\tau$ where the order of limits is crucial. The result was $\Omega_\infty = 0.25 \pm 0.04$, in good agreement with the $1/N$ result at $N = 3$. Finally, there is an analogy between Ω_∞ and another univer-

sal number discussed recently - the universal conductivity, σ_Q , at the superfluid-insulator transition [14,19].

We turn next to small x . The $N = \infty$ result (2) gives the leading term $\Omega_Q(x \rightarrow 0) = 1/(\pi x)$ which implies $\chi_u(T = 0) = 2g^2\mu_B^2\rho_s/(\hbar^2c^2N) \equiv (2/N)\chi_\perp$, where $\chi_\perp$ is the transverse susceptibility. This is in fact equal to the exact result expected from rotational averaging of an ordered quantum $O(N)$ sigma model [3] - we have indeed found no corrections in the $1/N$ expansion at $T = 0$. Furthermore, it was shown in Ref. [3] that there are no T -dependent corrections to the isotropic χ_u in a classical lattice rotator model. In contrast, for our quantum $O(N)$ sigma model, the $N = \infty$ result contains a term linear in T at small T . In the $1/N$ expansion of this quantum model, the classical contributions appear as $\log x/N$ terms; however, as expected, the coefficient of $\log x/N$ in χ_u was found to vanish. These results imply

$$\Omega_Q(x \rightarrow 0) = 1/(\pi x) + \Gamma_N + \dots \quad (4)$$

where $\Gamma_N = 1/\pi + \mathcal{O}(1/N)$ is a universal number; some x dependence in Γ_N at order $1/N^2$ is not ruled out.

Correlation Length, ξ : The scaling dimension of ξ is -1, and the finite-size scaling result for $\xi(T)$ is therefore:

$$\xi^{-1}(T) = (k_B T/(\hbar c))X_Q(x), \quad (5)$$

where $X_Q(x)$ is a universal function. As for χ_u , there are no non-universal factors on the right hand side. The numerical results for X_Q depend on the precise definition chosen for ξ : we use $\xi^2 = -(1/S(k))(\partial S/\partial k^2)|_{k=0}$ where $S(k)$ is the equal-time staggered spin structure factor (this definition is slightly different from that used in Ref. [3]). At $N = \infty$, we found

$$X_Q^{N=\infty}(x) = F(x)\sqrt{2/[1 + F(x)/\sinh(F(x))]} \quad (6)$$

For large x , the properties of ξ^{-1} are similar to those of χ_u . The function $X_Q(x)$ is expected to be analytic at $x = \infty$ with $X_Q(x \rightarrow \infty) = X_\infty + X_1/x + \dots$; a plot of $\xi^{-1}(T)$

vs. T will be straight line at large T with a universal slope and intercept, whose values are related to X_∞ and X_1 respectively. At $N = \infty$ we find $X_\infty = 0.998, X_1 = -0.990$.

For small x , the $N = \infty$ result (6) gives $X_Q(x \rightarrow 0) = e^{-1/x}$. However, unlike χ_u , the renormalized-classical spin fluctuations make a strong contribution to ξ , thus requiring careful consideration of the $\log x/N$ terms in the $1/N$ expansion. We identified terms to order $(\log x/N)^2$, exponentiated them and found

$$X_Q(x \rightarrow 0) = Y_N x^{-1/(N-2)} e^{-N/((N-2)x)} \quad (7)$$

where Y_N is a universal constant, and $\lim_{N \rightarrow \infty} Y_N = 1$. The analysis of Chakravarty *et al.* [3], valid for $k_B T \ll \rho_s$ but ρ_s/J arbitrary, obtained an identical functional form for $\xi(T)$, but with Y_N replaced by a non-universal, regularization dependent prefactor whose determination for a square-lattice $2D$ $S = 1/2$ Heisenberg antiferromagnet required a lengthy calculation. Our new result here is that, in the lowest order in ρ_s/J , this prefactor is also universal, and can therefore be evaluated in any convenient regularization scheme.

NMR relaxation rate, $1/T_1$: The relaxation of nuclear spins coupled to the antiferromagnetic order parameter (*e.g.* Cu nuclear spins in La_2CuO_4) is given by $1/T_1(T) = \lim_{\omega \rightarrow 0} 2\tilde{A}_\pi^2 k_B T / (\hbar \omega) \int d^2 k / (4\pi^2) \chi''(k, \omega)$, where $\chi''(k, \omega)$ is the imaginary part of the dynamic staggered susceptibility of the underlying quantum antiferromagnet, and $\tilde{A}_\pi$ is the bare hyperfine coupling. This determines the scaling dimension of $1/T_1$ at the quantum fixed-point to be η , the critical exponent associated with spin correlations at criticality: $\eta = 8/(3\pi^2 N) - 512/(27\pi^4 N^2) + \dots$ in a $1/N$ expansion [22] and the best current value at $N = 3$ is $\eta \approx 0.028$ [18]. The finite-size scaling form for $1/T_1$ can be shown to be

$$1/T_1(T) = (2\tilde{A}_\pi^2 N_0^2 / \rho_s) x^\eta R_Q(x) \quad (8)$$

where $R_Q(x)$ is a completely universal function. Ref. [21] used the renormalized hyperfine coupling A_π which is $A_\pi = \tilde{A}_\pi N_0$. Note the complete absence of non-universal normalization factors in (8).

We now consider the limiting behavior of $R_Q(x)$ for large and small x . As before, at large x , $R_Q(x \rightarrow \infty) = R_\infty$, a positive constant; the small value of η then implies that $1/T_1$

is *essentially* T independent at high T . To leading order in $1/N$, R_∞ can be deduced from the results of Ref. [11] to be $R_\infty = 0.06/N$. Note the factor of $1/N$ - $\chi''(k, \omega)$ is finite at $\omega \rightarrow 0$ only due to the self-energy corrections. At small x , dynamical scaling [23] predicts that $R_Q(x) \propto \xi(x)$. The $1/N$ expansion is again singular when $x \ll 1$ and we will not discuss it here.

Comparison with numerical and experimental results: We have so far presented general scaling forms for the magnetic properties of a two-dimensional quantum antiferromagnet which has $\rho_s \ll J$. Explicit scaling functions can be calculated at $N = \infty$, and examination of $1/N$ corrections has been limited to those for Ω_∞ . These corrections were however quite small, and we expect, in general, that $1/N$ expansion is robust and numerically quite accurate for large values of x . On the other hand, at small x , the $1/N$ expansion is logarithmically singular, and eventually changes the leading singularity in some of the scaling functions at $x = 0$; the final low- T behavior is the same as that in the renormalized-classical scaling theory of Ref [3]. The crossover between small and large x should occur for x around unity. Thus for $x \geq 1$ (but such that long-wavelength description is still valid), it is quite likely that $1/N$ expansion will describe the experimental data better than the renormalized-classical theory, which, strictly speaking, is valid only for $x \ll 1$. In a square lattice, nearest-neighbor, $S = 1/2$ Heisenberg antiferromagnet, $2\pi\rho_s \approx 1.13J$ (Ref [24]) and we therefore expect that our large- N , large x results should work for $x \geq 1$, i.e., for $k_B T \geq 0.35J$.

The absence of any renormalized-classical corrections to χ_u makes it an ideal candidate for testing our theory; the $1/N$ expansion should become accurate even at fairly small values of x . We start with the numerical results for $\chi_u(T)$ on the square lattice $S = 1/2$ antiferromagnet. There have been high- T series expansions [8], quantum Monté-Carlo [9] and finite cluster calculations [10]. Their results all show that $\chi_u(T)$ obeys a Curie-Weiss law at high T , reaches a maximum at $k_B T \sim J$ and then falls to a finite value at $T = 0$ which is rather close to the rotationally averaged $1/S$ result $(\hbar/g\mu_B)^2 \chi_u(T = 0) \approx 0.04/Ja^2$, where a is the lattice spacing. For $0.35J < T < 0.55J$, both series expansions [8] and Monte-Carlo [9] calculations report a *linear* T dependence of $\chi_u(T)$ (Fig.1). Also plotted is our

theoretical prediction of Eqns (2,3) which, over the range of x values used in the figure, is well approximated by $(\hbar/g\mu_B)^2(Ja^2\chi_u(T)) \approx 0.037x(1 + \alpha/x)$, $\alpha = 0.8 + \mathcal{O}(1/N)$. This is remarkably close to the best fit to the data of Ref. [9] which gives $0.037x(1 + 0.775/x)$.

We consider next measurements of $\chi_u(T)$ in weakly doped $La_{2-\delta}Sr_\delta CuO_4$. The interpretation of the experimental data even above the zero-doping T_N requires caution because one has to subtract Van-Vleck, core and diamagnetic contributions from the measured $\chi_u(T)$. Besides, at nonzero doping, a Pauli-like contribution from valence fermions should also be subtracted. Nevertheless, after subtraction was carried out, it was found [5,25] that there is a large amount of universality in the susceptibility data at different doping concentrations and the measured susceptibility is clearly *linear* in T in the temperature interval $400 - 700K$ (i.e., $0.3J - 0.5J$ for $J \sim 0.12\text{ev}$). The measured slope of $(\hbar/g\mu_B)^2(Ja^2\chi_u(T))$ vs. x is about 0.04 which is very close to our result (0.037).

Now the ^{63}Cu spin-lattice relaxation rate, $1/T_1$, in La_2CuO_4 . At very low T (x small), the theory of Ref. [21] predicts that $1/T_1 \propto e^{-3/x}$; this is consistent with recent observations [7]. However, the present theory predicts that $1/T_1$ becomes nearly T independent for $x > 1$ or $T > 0.35J$. This has in fact already been observed in series expansions [8] and finite cluster calculations [10] for the square lattice antiferromagnet. More importantly, a flattening in $1/T_1(T)$ has recently been observed in the experiments on La_2CuO_4 [7]. We calculated, from our results above, the limiting large T value of $1/T_1$ for the same values of parameters as were used in the low- T fit [7] and found $1/T_1 \approx 3.3 \times 10^3 \text{sec}^{-1}$; this is in good agreement with the experimental result $1/T_1 \approx 2.7 \times 10^3 \text{sec}^{-1}$. Furthermore, the experimental T range over which $1/T_1$ is nearly T independent increases upon doping. This is also consistent with our results because ρ_s is expected to decrease with doping, thus pushing the system into larger x for the same T .

The agreement between our theory and the data for ξ is however not so good. Detailed measurements of ξ in La_2CuO_4 have been performed at low T , where the system is in the renormalized-classical region [6]. At the highest experimentally accessible T ($= 560K$ for $J = 1460K$), our result $\xi^{-1} = 0.023\text{\AA}^{-1}$ is not far from the experimental value of

$\xi^{-1} = 0.03\text{\AA}^{-1}$. We also compared our results with the numerical data for ξ at higher T [9,26]. For $T > 0.35J$ this data obeys quite well $\xi^{-1} \propto x(1 - \gamma/x)$ where γ is close to one. However, the overall factor in ξ in the fit is close to twice our $N = \infty$ result. This discrepancy is probably due to the fact that the strong singular corrections in $X_Q(x)$ at small x , cause the crossover from small to large x behavior to occur at a larger x . Note however that the Monté-Carlo calculations in the quantum-critical region [27] yield the value of $X_\infty = 1.25$, which is close to our $N = \infty$ result of $X_\infty = 0.998$.

To conclude, we have considered in this paper the magnetic properties of two-dimensional quantum antiferromagnets. We argued that there exists a T range where the classical low- T description is no longer valid and the behavior of observables is governed by the renormalization-group flows near the $T = 0$ quantum fixed-point. A comparison with the experimental data for the uniform susceptibility and ^{63}Cu spin-lattice relaxation rate shows that the intermediate behavior has been observed in the range $0.35J < T < 0.55J$ in La_2CuO_4 .

We thank N. Read and A. Sokol for discussions. This work has been supported by NSF Grant DMR88-57228.

REFERENCES

- [1] See e.g, S. Chakravarty in *High-Temperature Superconductivity*, eds. K. Bedell, D. Coffey, D.E. Meltzer, D. Pines and J.R. Schrieffer, Addison-Wesley, p.136 (1990).
- [2] E.Manousakis, Rev. Mod. Phys, **63**, 1 (1991).
- [3] S. Chakravarty, B.I. Halperin and D.R. Nelson, Phys. Rev. B **39**, 2344 (1989).
- [4] C. Broholm *et. al.*, Phys. Rev. Lett. **65**, 3173 (1991); G. Aeppli, C. Broholm, and A. Ramirez in Proceedings of the Kagomé Workshop, NEC Research Institute, Princeton, NJ (unpublished).
- [5] D.C. Johnson, Phys. Rev. Lett, **62**, 957 (1989).
- [6] Y. Endoh et al, Phys. Rev. B **37**, 7443 (1988); K. Yamada et al, Phys. Rev. B **40**, 4557 (1989).
- [7] T. Imai, C.P. Slichter, K. Yoshimura and K. Kosuge, preprint.
- [8] R.R.P. Singh and M. Gelfand, Phys. Rev. B **42**, 966 (1990).
- [9] H.Q. Ding and M. Makivic, Phys. Rev. Lett, **64**, 1449 (1990); Phys. Rev. B **43**, 3662 (1990).
- [10] A. Sokol, S. Bassi and E. Gagliano, in preparation.
- [11] S. Sachdev and J. Ye, Phys. Rev. Lett, **69**, 2411 (1992).
- [12] Randomness is expected to be a relevant perturbation at the $T = 0$ quantum fixed-point [11]. Nevertheless, it is probably innocuous at the rather high T 's at which experimental comparisons are made in this paper.
- [13] B.D. Josephson, Phys. Lett. **21**, 608 (1966); D. Stauffer, M. Ferer, and M. Wortis, Phys. Rev. Lett. **29**, 345 (1972).
- [14] M.P.A. Fisher, G. Grinstein, and S.M. Girvin, Phys. Rev. Lett. **64**, 587 (1990); M.-C.

- Cha *et.al.*, Phys. Rev. B **44**, 6883 (1991).
- [15] D.S. Fisher, Phys. Rev. B **39**, 11783 (1989).
- [16] M.N. Barber in *Phase Transitions and Critical Phenomena*, ed. C. Domb and J. Lebowitz, v. 8, pg. 145, Acad. Press (New York).
- [17] A.M. Polyakov, *Gauge Fields and Strings*, Harwood, New York (1987).
- [18] C. Holm and W. Janke, preprint; P. Peczak, A.M. Ferrenberg, and D.P. Landau, Phys. Rev. B **43**, 6087 (1991).
- [19] At the quantum fixed-point, we have $\Omega_\infty \sim \chi_u(T)/T \sim \rho_\tau(T, \omega = 0)/T$, while $\sigma_Q \sim \rho_s(T = 0, \omega)/(i\omega)$, where ω is the measurement frequency. The two quantities are thus related by a Lorentz rotation and the interchange of ω and T . However, computation of Ω_∞ requires use of finite temperatures, which makes the analysis considerably more difficult than that for σ_Q .
- [20] D.R. Nelson and R.A. Pelcovits, Phys. Rev. B **16**, 2191 (1977).
- [21] S. Chakravarty and R. Orbach, Phys. Rev. Lett **64**, 224 (1990).
- [22] S-k. Ma, *Modern Theory of Critical Phenomena*, Benjamin/Cummings, Reading (1976); R. Abe, Prog. Theor. Phys. **49**, 1877 (1973).
- [23] B.I. Halperin and P.C. Hohenberg, Phys. Rev. **177**, 952 (1969).
- [24] T. Oguchi, Phys. Rev, **117**, 117 (1960).
- [25] A. Millis and H. Monien, preprint.
- [26] E. Manousakis and R. Salvador, Phys. Rev. B **39**, 575 (1989); E. Manousakis, Phys. Rev. B **45**, 7570, (1992).
- [27] E. Manousakis and R. Salvador, Phys. Rev B **40**, 2205 (1989).

FIGURES

FIG. 1. ‘Experimental’ [9] (squares) and theoretical (line) results for the uniform susceptibility $\overline{\chi}_u = (3J(a\hbar/g\mu_B)^2)\chi_u$ of a square lattice spin-1/2 Heisenberg antiferromagnet (a is the lattice spacing). There are *no* adjustable parameters in the theoretical result (1). Over the range of x plotted, the function $\Omega_Q(x)$ is very close to its large x behavior $\Omega_Q(x) \approx \Omega_\infty(1 + 0.8/x)$. We used this large x result with Ω_∞ from (3) at $N = 3$. The theoretical and experimental slopes agree remarkably well. The good agreement in the intercept is somewhat surprising as its theoretical value ($= 0.8$) is known only at $N = \infty$.